

Paintworks Specification GS 105.8

| | |
|------------------|---|
| System | GranoSpray-On Fine® Impact - formerly GranoClassic® Spray Impact |
| Substrate | Exterior – New and uncoated compressed fibre cement (CFC) |
| Category | Premium Texture – Water Based |

Product Features

GranoSpray-On Fine® is a spray applied pigmented acrylic texture coating giving an elegant yet traditional stone-like finish.

Surface Preparation

Substrate must be free from dirt, dust, oil, grease, mould or any other contaminants that may affect adhesion.

Ensure all sheets are installed as per the manufacturers specification and installation manual. Examine sheets to ensure there is no possibility of future sheet movement.

Ensure that any jointing compounds used are fully cured.

Repair damaged areas with GranoPatch® Smooth (G1.04), or GranoPatch® Spackle (G1.05), sand back, dust off.

| Application Details | Data Sheet | Coverage | Film Thickness (microns) | | Dry Times | |
|---|------------|-------------------------|--------------------------|-----|-----------|----------|
| | | | Wet | Dry | Touch | Topcoat |
| First Coat: GranoPrime® (equipment: roller or spray) | G1.02 | 0.08 L/M ² | 80 | 20 | 2 hours | 6 hours |
| Second Coat: GranoSpray-On Fine® (equipment: hopper spray gun) | G2.08 | 2.00 Kg/ M ² | 1020 | 670 | 4 hours | 24 hours |
| Third Coat: GranoImpact® (equipment: roller or spray) | G2.01 | 0.25 L/M ² | 250 | 120 | 4 hours | 6 hours |

Recommended Uses For exterior or interior use.

Additional Notes

Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, it must be carried out according to Watty's recommendations.

It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Watty Granosite products and systems, to validate full material warranty conditions.

Caution

Provide adequate ventilation during use.

Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

1. This information is provided with respect to the listed Granosite products. Watty recommends that:

(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty cannot guarantee that the information provided is wholly comprehensive.

3. Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty Office.

4. To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.