

# Paintworks Specification GS 106.9

<b>System</b>	<b>GranoSpray-On Fine® Membrane - formerly GranoClassic® Spray Membrane</b>
<b>Substrate</b>	<b>Exterior – New and uncoated Ritek Sheets</b>
<b>Category</b>	<b>Premium Texture – Water Based</b>

## Product Features

GranoSpray-On Fine® is a spray applied pigmented acrylic texture coating giving an elegant yet traditional stone-like finish.

## Surface Preparation

Substrate must be free from dirt, dust, oil, grease, mould or any other contaminants that may affect adhesion.

Ensure Fibre Cement Sheets are securely fixed in accordance with manufacturer's specifications. Examine sheets to ensure that there is no possibility of future sheet movement.

### Jooints:

Thoroughly mix 20% grey builder's cement by volume into the GranoFlex® (G1.15). Place GranoMesh into the recessed area and, trowel GranoFlex® (G1.15) over the GranoMesh ensuring that the mesh is fully encapsulated. Trowel surface flush with sheet face. Allow to dry for 24 hours.

Application Details	Data Sheet	Coverage M <sup>2</sup> /L	Film Thickness (microns)		Dry Times	
			Wet	Dry	Touch	Topcoat
First Coat: <b>GranoReady Render®</b> (equipment: Stainless Steel Trowel)	G1.12	1.50Kg/M <sup>2</sup> (per 1mm)	1100	730	4 hours	24 hours
Second Coat: <b>GranoSpray-On Fine®</b> (equipment: hopper spray gun)	G2.08	2.00 Kg/M <sup>2</sup>	1020	670	4 hours	24 hours
Third Coat: <b>GranoSkin® Membrane</b> (equipment: roller or spray)	G2.14	0.25L/M <sup>2</sup>	250	125	4 hours	6 hours

## Additional Notes

Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, it must be carried out according to Watty's recommendations.

It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Granosite products and systems, to validate full material warranty conditions.

## Caution

Provide adequate ventilation during use.

Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

Ritek® is a registered trademark of Building Solutions Pty Ltd

## 1. This information is provided with respect to the listed Granosite products. Watty recommends that:

- (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
2. The information in this technical data sheet was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty cannot guarantee that the information provided is wholly comprehensive.
3. Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty Office.
4. To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.