

# Paintworks Specification GS 132.9

<b>System</b>	<b>GranoMarble Fast™ Matt</b>
<b>Substrate</b>	<b>Exterior – New and uncoated ExoTec Façade Panel™</b>
<b>Category</b>	Premium Texture – Water Based

## Product Features

GranoMarble Fast™ is an economical and long lasting means for creating a lightweight stone-like finish over most cementitious substrates. GranoMarble Fast™ is applied by trowel, creating a sophisticated grainy textured finish.

## Surface Preparation

Substrate must be free from dirt, dust, oil, grease, mould or any other contaminants that may affect adhesion.

Ensure sheets are fixed as per the James Hardie ExoTec Façade Panel™ Fixing Manual. Examine sheets to ensure that there is no possibility of future sheet movement.

Repair damaged areas with GranoPatch® Smooth (G1.04), or GranoPatch® Spackle (G1.05), sand back, dust off.

Application Details	Data Sheet	Coverage	Film Thickness (microns)		Dry Times	
			Wet	Dry	Touch	Topcoat
First Coat: <b>GranoBasecoat® #</b> <i>(equipment: roller or spray)</i>	G1.11	0.12 L/M <sup>2</sup>	120	50	2 hours	4 hours
Second Coat: <b>GranoMarble Fast™</b> <i>(equipment: Stainless Steel &amp; Red Plastic Trowel)</i>	G2.23	2.21 Kg/ M <sup>2</sup>	1400	900	4 hours	24 hours

**Recommended Uses** For exterior or interior use.

## Additional Notes

Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, it must be carried out according to Watty's recommendations.

It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Watty Granosite products and systems, to validate full material warranty conditions.

**#** When leaving GranoMarble Fast™ as a matt finish, the GranoBasecoat® must be tinted to the same colour as the topcoat.

When using matt systems consistency of colour between different drums and batches cannot be guaranteed. Applicator best practice of ordering in single batch lots and boxing individual drums is required. Boxed drum lots are required for any single elevation and each elevation must be completed once it is started. Day joints are not acceptable.

## Caution

Provide adequate ventilation during use.

Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

ExoTec® is a registered trademark of James Hardie International Finance B.V.

### 1. This information is provided with respect to the listed Granosite products. Watty recommends that:

(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty cannot guarantee that the information provided is wholly comprehensive.

3. Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty Office.

4. To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.