

# Paintworks Specification GS 170.5

<b>System</b>	<b>GranoSkin® Membrane Low Profile</b>
<b>Substrate</b>	<b>Exterior – New and uncoated off form concrete</b>
<b>Category</b>	<b>Premium Texture – Water Based</b>

## Product Features

GranoSkin® Membrane is a single-pack high performance elastomeric acrylic coating for waterproofing applications.

## Surface Preparation

Ensure all new cementitious substrates are fully cured prior to coating. Typically this may take a minimum of 4-6 weeks. There must be less than 15% moisture content in the surface at the time of application to ensure optimum coating performance. The surface must not be subject to frequent wetting or hydrostatic pressure. Any foreign material that may affect adhesion must be removed prior to coating. Grind off any protruding formwork joints.

**Patching & Skimming Imperfections:** Examine surfaces closely for air holes and imperfections, fill or skim as required with a GranoPatch® Smooth (G1.04) or GranoPatch® Spackle (G1.05), block down, allow to dry, sand back and dust off.

**Rendering:** Apply GranoBond® (G1.01) keycoat system liberally (0.5L/m<sup>2</sup>) to surface and allow to dry for 24 hours. Render surface with the appropriate GranoRender®. Allow to cure 7 days.

**Priming:** Off form concrete with a very hard or smooth surface must be primed with GranoPrime S (G1.03).

Application Details	Data Sheet	Coverage	Film Thickness (microns)		Dry Times	
			Wet	Dry	Touch	Topcoat
First Coat: <b>GranoPrime®</b> (equipment: roller or spray)	G1.02	0.08 L/M <sup>2</sup>	80	20	2 hours	6 hours
Second Coat: <b>GranoSkin® Membrane</b> (equipment: 10 – 12mm pile roller)	G2.14	0.33 L/M <sup>2</sup>	330	165	4 hours	6 hours
Third Coat: <b>GranoSkin® Membrane</b> (equipment: 10 – 12mm pile roller)	G2.14	0.33 L/M <sup>2</sup>	330	165	4 hours	6 hours

**Recommended Uses** For exterior or interior use.

## Additional Notes

Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, it must be carried out according to Watty's recommendations.

It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Watty's Granosite products and systems, to validate full material warranty conditions.

## Caution

Provide adequate ventilation during use.

Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

## 1. This information is provided with respect to the listed Granosite products. Watty recommends that:

- (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
- The information in this technical data sheet was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty cannot guarantee that the information provided is wholly comprehensive.
- Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty Office.
- To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.