

# Paintworks Specification GS 173.3

<b>System</b>	GranoSahara Fine® Roll-on / Brush Membrane
<b>Substrate</b>	Exterior – Change existing texture
<b>Category</b>	Premium Texture – Water Based

## Product Features

GranoSahara Fine® is an acrylic coating applied by roller, brush or lambswool mitt in one or two coats to give a convenient and economical means for simulating a sandy or 'bagged' finish.

## Surface Preparation

Remove all coating, which is blistered, loose, or flaking back to a firm edge. This can be achieved through high-pressure water cleaning at 500-1000psi. Allow to dry.

Repair and replace any areas which are not sound (eg. Concrete cancer / spalling, drummy render etc).

Skim entire surface with GranoPatch® Spackle (G1.05) applying one coat to the entire surface. Allow 24 hours to dry. Apply an additional coat of GranoPatch® Spackle (G1.05) if required.

Application Details	Data Sheet	Coverage	Film Thickness (microns)		Dry Times	
			Wet	Dry	Touch	Topcoat
First Coat: <b>GranoPrime®</b> (optional) <i>(equipment: roller or spray)</i>	G1.02	0.08 L/M <sup>2</sup>	80	20	2 hours	6 hours
Second Coat: <b>GranoSahara Fine®</b> <i>(equipment: 10-12mm pile roller or block brush)</i>	G2.19	0.40 L/M <sup>2</sup>	400	195	4 hours	12 hours
Third Coat: <b>GranoSkin® Membrane</b> <i>(equipment: roller or spray)</i>	G2.14	0.20L/M <sup>2</sup>	200	100	4 hours	6 hours

**Recommended Uses** For exterior or interior use.

## Additional Notes

Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, it must be carried out according to Wattyl's recommendations.

It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Wattyl Granosite products and systems, to validate full material warranty conditions.

Note: The **Brush** style is achieved by using a block brush to pattern the GranoSahara Fine® whilst still wet.

## Caution

Provide adequate ventilation during use.

Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

### 1. This information is provided with respect to the listed Granosite products. Wattyl recommends that:

- (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
- The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.
- Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office.
- To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.