

Paintworks Specification GS 173.6

System	GranoSahara Fine® Roll-on / Brush Membrane
Substrate	Exterior – New and uncoated brick & concrete block
Category	Premium Texture – Water Based

Product Features

GranoSahara Fine® is an acrylic coating applied by roller, brush or lambswool mitt to give a convenient and economical means for simulating a sandy or 'bagged' finish.

Surface Preparation

Substrate must be free from dirt, dust, oil, grease, mould or any other contaminants that may affect adhesion. All scaling, efflorescence, mould, mastic compound or any other foreign material must be removed prior to painting.

Remove all traces of loosely adhering material by scraping, grinding or wire brushing, etc.

Render surface with the appropriate GranoRender®. Allow to cure 7 days. There must be less than 15% moisture content in the surface at the time of application to ensure optimum coating performance.

For raked joints apply in two coats first filling the joints flush with brickwork then skim coating the whole surface.

For flush joints apply one coat directly to the surface.

Application Details	Data Sheet	Coverage	Film Thickness (microns)		Dry Times	
			Wet	Dry	Touch	Topcoat
First Coat: GranoPrime® (optional) <i>(equipment: roller or spray)</i>	G1.02	0.08 L/M ²	80	20	2 hours	6 hours
Second Coat: GranoSahara Fine® <i>(equipment: 10-12mm pile roller or block brush)</i>	G2.19	0.40 L/M ²	400	195	4 hours	12 hours
Third Coat: GranoSkin® Membrane <i>(equipment: roller or spray)</i>	G2.14	0.20L/M ²	200	100	4 hours	6 hours

Recommended Uses For exterior or interior use.

Additional Notes

Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, it must be carried out according to Watty's recommendations.

It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Watty Granosite products and systems, to validate full material warranty conditions.

Note: The **Brush** style is achieved by using a block brush to pattern the GranoSahara Fine® whilst still wet.

Caution

Provide adequate ventilation during use.

Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

ExoTec® is a registered trademark of James Hardie International Finance B.V.

1. This information is provided with respect to the listed Granosite products. Watty recommends that:

(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty cannot guarantee that the information provided is wholly comprehensive.

3. Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty Office.

4. To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.