

# Paintworks Specification GS 206.3

<b>System</b>	<b>GranoTrowl® 3mm Membrane</b>
<b>Substrate</b>	<b>Exterior – New and uncoated brick &amp; concrete block</b>
<b>Category</b>	Premium Texture – Water Based

## Product Features

GranoTrowl® is a range of durable, high build acrylic texture coating systems. They are trowel applied to produce Travertin or Circular styles in several thicknesses and are overcoated with GranoImpact® (G2.01) or GranoSkin® Membrane (G2.14).

## Surface Preparation

Substrate must be free from dirt, dust, oil, grease, mould or any other contaminants that may affect adhesion. All scaling, efflorescence, mould, mastic compound or any other foreign material must be removed prior to painting.

Remove all traces of loosely adhering material by scraping, grinding or wire brushing, etc.

Render surface with the appropriate GranoRender®. Allow to cure 7 days. There must be less than 15% moisture content in the surface at the time of application to ensure optimum coating performance.

For raked joints apply in two coats first filling the joints flush with brickwork then skim coating the whole surface.

For flush joints apply one coat directly to the surface.

Application Details	Data Sheet	Coverage	Film Thickness (microns)		Dry Times	
			Wet	Dry	Touch	Topcoat
First Coat: <b>GranoPrime®</b> <i>(equipment: roller or spray)</i>	G1.02	0.08 L/M <sup>2</sup>	80	20	2 hours	4 hours
Second Coat: <b>GranoTrowl® 3mm</b> <i>(equipment: stainless steel trowel &amp; styropor float)</i>	G2.07	4.00Kg/M <sup>2</sup>	2020	1340	4 hours	24 hours
Third Coat: <b>GranoSkin® Membrane</b> <i>(equipment: roller or spray)</i>	G2.14	0.30L/M <sup>2</sup>	300	150	4 hours	6 hours

**Recommended Uses** For exterior or interior use.

## Additional Notes

Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, it must be carried out according to Wattyl's recommendations.

It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Wattyl Granosite products and systems, to validate full material warranty conditions.

## Caution

Provide adequate ventilation during use.

Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

### 1. This information is provided with respect to the listed Granosite products. Wattyl recommends that:

- (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
- The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.
- Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office.
- To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.