

Paintworks Specification GS 334.2

System	GranoRoll-On Coarse® Impact – formerly Granosite Texture Coarse™ Impact
Substrate	Exterior – Previously painted water based / acrylic exterior surfaces
Category	Premium Texture – Water Based

Product Features

GranoRoll-On Coarse™ is an acrylic, high performance coating applied by black texture or spaghetti roller to achieve a medium profiled texture.

GranoRoll-On Coarse™ must be top coated with GranoImpact® (G2.01).

Surface Preparation

Remove all paint, which is soft, blistered, loose, or flaking back to a firm edge. Areas where the previous coatings were powdery, remove all powder. Wash all surfaces with mild detergent to remove contaminants, rinse with clean water. Fill any cracks, holes or imperfections with GranoPatch® Smooth (G1.04), allow to dry. Sand back and dust off.

Application Details	Data Sheet	Coverage	Film Thickness (microns)		Dry Times	
			Wet	Dry	Touch	Topcoat
First Coat: GranoPrime® (equipment: roller or spray)	G1.02	0.08 L/M ²	80	20	2 hours	6 hours
Second Coat: GranoRoll-On Coarse™ (equipment: black texture roller)	G2.20	0.8 L/M ²	800	500	4 hours	24 hours
Third Coat: GranoImpact® (equipment: roller or spray)	G2.01	0.20L/M ²	200	95	4 hours	6 hours

Recommended Uses For exterior or interior use.

Additional Notes

Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, it must be carried out according to Watty's recommendations.

It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Watty Granosite products and systems, to validate full material warranty conditions.

Caution

Provide adequate ventilation during use.

Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

1. This information is provided with respect to the listed Granosite products. Watty recommends that:

(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty cannot guarantee that the information provided is wholly comprehensive.

3. Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty Office.

4. To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.