

# Paintworks Specification GS 350.8

<b>System</b>	<b>GranoMarble Fast™ Shield</b>
<b>Substrate</b>	<b>Exterior – New and uncoated Autoclaved Aerated Concrete (AAC)</b>
<b>Category</b>	<b>Premium Texture – Water Based</b>

## Product Features

GranoMarble Fast™ is an economical and long lasting means for creating a lightweight stone-like finish over most cementitious substrates. GranoMarble Fast™ is applied by trowel, creating a sophisticated grainy textured finish.

## Surface Preparation

All scaling, efflorescence, mastic compound or any other contaminants that may affect adhesion must be removed prior to coating. Remove all traces of loosely adhering material by scraping and wire brushing. Sweep or air blow remaining particles from joints. Repair imperfections with GranoPatch® Smooth (G1.04) or GranoPatch® Spackle (G1.05), allow to dry, sand back (G.04) and dust off.

### Autoclaved Aerated Concrete (AAC) Blocks

Seal surface with GranoBond® Sealcoat (G1.01), applying an even coat to the entire surface. Alternatively, temper the surface by wetting down with water to ensure the surface porosity of AAC does not hinder curing of the render.

Render surface with the appropriate GranoRender®, applying one coat to the entire surface. Allow to dry.

### Autoclaved Aerated concrete (AAC) – CSR Power Panels®

Seal surface with GranoBond® Sealcoat (G1.01) applying an even coat to the entire surface. Alternatively, temper the surface by wetting down with water to ensure the surface porosity of AAC does not hinder curing of the render.

Render surface with the appropriate GranoRender®, applying one coat to the entire surface. Allow to dry.

Alternatively, render CSR Power Panel® surfaces with GranoReady® Render (G1.12) or GranoSponge Fine Acrylic (G1.21), applying one coat to the entire surface. Allow to dry. A second application of GranoReady® Render may be required to achieve a consistent texture. For CSR Power Panel® walls which require significant patching and remediation before being coated, the appropriate GranoShield® Matt High Profile system specification must be used.

Application Details	Data Sheet	Coverage M <sup>2</sup> /L	Film Thickness (microns)		Dry Times	
			Wet	Dry	Touch	Topcoat
First Coat: <b>GranoPrime™</b> (equipment: roller or spray)	G1.02	0.08 L/M <sup>2</sup>	80	20	2 hours	4 hours
Second Coat: <b>GranoMarble Fast™</b> (equipment: Stainless Steel & Red Plastic Trowel)	G2.23	2.21 Kg/ M <sup>2</sup>	1400	900	4 hours	24 hours
Third Coat: <b>GranoShield® Matt</b> (equipment: 10 – 12mm pile roller)	G2.27	0.25 L/M <sup>2</sup>	250	117	4 hours	6 hours

**Recommended Uses** For exterior or interior use.

## Additional Notes

Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, it must be carried out according to Watty's recommendations.

It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Watty Granosite products and systems, to validate full material warranty conditions.

## Caution

Provide adequate ventilation during use.

Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

---

**1. This information is provided with respect to the listed Granosite products. Wattyl recommends that:**

(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavors to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.

3. Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office.

4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.

---

**Granosite**

Granosite is a registered trademark of WATTYL PTY LTD (ABN 46 004 580 063) INFORMATION HOTLINE Ph: 132101 (AUSTRALIA)