



DESCRIPTION

- a pigmented, two-pack acid-catalysed coating for interior timber

PRINCIPAL CHARACTERISTICS

- excellent finish
- high-solids, with low odour
- excellent sanding properties
- high resistance to abrasion, hot water, common household chemicals such as nail polish, vegetable oil and beverage alcohol
- suitable for small and large-scale factory finishing for domestic and commercial applications
- suitable for interior use only

Note: We advise that you test this product to determine if it is suitable for your particular use.

COLOUR AND GLOSS

- white, full colour offer available through the Ultraint[®] tinting system, full gloss and satin (30%)
- satin colours available using Matting Agent 600

BASIC DATA AT 25°C and 50% RELATIVE HUMIDITY

- mix ratio 9A:1B by volume
- dust free 20 minutes
- touch-dry 30 minutes
- sandable 3 hours
- recoat 3 hours - better hold out is obtained if the film is left to cure overnight
- practical spreading rate 8-10 m²/L
- shelf life (cool, dry place) at least 12 months in unopened container

SURFACE PREPARATION

- all surfaces must be free from wax, silicone, oil and other contaminants
- fill holes and minor imperfections with WattyI Full Stop Timber Putty.
- sand smooth with 180-240 grade fre-cut paper, and remove all sanding dust
- if required, stain the surface using WattyI Craftsman[®] Dye Stain Fast, Slow or Craftsman Pigmented Stain
- Do not use Woodgrain Filler under Acid Cat
- filling/sealing, apply a double-pass of Acid Cat Undercoat to the desired wet film thickness. Allow to dry, and sand (refer to the relevant data sheets for further details on undercoat application and sanding recommendations)
- Acid Cat Topcoat may be used as a self-sealer, but better sanding and grain filling will be achieved by using Acid Cat Sealer

INSTRUCTIONS FOR USE

- mixing ratio by volume: 9A:1B
- induction time- none
- potlife at 25°C - 48 hours (when thinned). Do not use after this time even if the mix is still liquid
- stir the components and mixed product well using a mechanical mixer
- apply a double-pass of Acid Cat Topcoat to give a wet film thickness of 75 - 125 microns. Allow to dry for a maximum of 5 minutes between passes. Allow to dry for 1 hour then sand with 320-400 fre-cut paper, removing all sanding dust. If desired, a second coat of Acid Cat Topcoat may be applied. Better hold out can be obtained if the sealer is left to dry overnight.
- **Warning:** Excessive builds on timber can lead to stress-cracking as the timber adjusts to its new conditions of temperature and moisture content. The recommended maximum total build is 150 microns (dry film) for the total system.
- for recommendations outside those contained in this data sheet, refer to WattyI



APPLICATION

- **CONVENTIONAL SPRAY**
 - recommended thinner Acid Cat Thinner
 - volume of thinner up to 15%
 - fluid nozzle 1.5 - 2.0 mm
 - pressure to the gun..... 250 - 350 kPa (30 - 50 psi)

- **AIR-ASSISTED AIRLESS SPRAY**
 - recommended thinner Acid Cat Thinner
 - volume of thinner up to 10%
 - fluid nozzle 0.23 - 0.28 mm (0.009-0.011 inch)
 - pump ratio 12 - 20 : 1
 - pump pressure 7 - 10 MPa (1000 - 1500 psi)

- **HVLP CONVENTIONAL**
 - recommended thinner Acid Cat Thinner
 - volume of thinner up to 10%
 - fluid nozzle 1.5 - 2.0 mm
 - pressure to the gun..... 250 - 350 kPa (30 - 50 psi)
 - pressure to air cap 70 kPa (10 psi)

- **CLEANING SOLVENT** Acid Cat Thinner

- **Note:** In hot conditions, replace some or all of the Acid Cat Thinner with Acid Cat Retarder

SAFETY PRECAUTIONS

- the catalyst used with this product contains an acid component, therefore the precautions stated on the label must be followed
- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

PACKAGING

Part A 4.5 litres, 18 litres
Part B 500mL, 2 litres

For the most up to date information contact WattyL Customer Service Hotline or visit the WattyL Website.

	Australia	New Zealand
CUSTOMER SERVICE HOTLINE	132 101	0800 735 551
WEBSITE	http://www.wattyL.com.au	http://www.wattyL.co.nz

WattyL and Ultratint are registered trademarks of WattyL Australia Pty Ltd.

1. This information is provided with respect to the listed WattyL products. WattyL recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by WattyL; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While WattyL endeavours to update this information and maintain the accuracy and currency of its contents, WattyL cannot guarantee that the information provided is wholly comprehensive. 3. For all product and non-product related information, WattyL recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest WattyL Office. 4. To the full extent permitted by law, WattyL's liability for breach of a condition or warranty implied into the contract for sale between WattyL and you by law is limited at WattyL's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.
WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)