



DESCRIPTION

- a premium quality acrylic modified alkyd gloss enamel

PRINCIPAL CHARACTERISTICS

- excellent exterior durability
- excellent flow and application properties
- very high gloss off-the-gun
- hard wearing
- may be readily touched-up or recoated after overnight drying
- long open time, offers good overspray absorption for spraying large items
- designed for use on cranes, harvesters, tractors, truck bodies, large machinery etc.

Note: We advise that you test this product to determine if it is suitable for your particular use.

COLOURS AND GLOSS

- AS2700 colour card, metallic colours, black - full gloss
- satin black, flat black

BASIC DATA AT 25° C and 50% RELATIVE HUMIDITY

- vehicle type acrylic modified alkyd
- typical film thickness (per coat) 25-45 microns (dry), 65-110 microns (wet)
- solids content approx. 38% by volume
- theoretical spreading rate 15 m²/L for 25 microns (dry)
- touch dry after 20-30 minutes (25 microns dry)
45 minutes - 1 hour (45 microns dry)
- dry to handle 4 hours (25 microns dry), 6 hours (45 microns dry)
- hard dry overnight
- recoat time within 4 hours, or after 16 hours
- shelf life (cool, dry place) at least 12 months in unopened container

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- best coating performance will be obtained with the highest degree of surface preparation
- degrease thoroughly to remove all oil, grease and other surface contaminants
- mild steel; remove all rust and any loose material by wire brush or mechanical sander, prime with WattyI All Purpose Primer
- non-ferrous metals, stainless steel, galvanised iron, ZINCALUME[®], COLORBOND[®]; abrade using a Scotch-Brite[®] pad or wet and dry sandpaper. Do not use steel wool. Prime with WattyI Super Etch[®] Primer
- suitable previous coat; mechanically sand with P220-240 grit sandpaper
- substrate temperature should be at least 3°C above dew point
- relative humidity should not exceed 85%



INSTRUCTIONS FOR USE

- stir thoroughly with a flat-bladed or mechanical stirrer before, and during use
- paint temperature must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in low sag resistance and slower cure
- adequate ventilation must be continuously maintained during application and curing
- for recommendations outside those contained in this data sheet, refer to Watty!

APPLICATION

- **AIRLESS SPRAY**
 - recommended thinner Industrial Enamel Thinner
 - volume of thinner up to 15%
 - nozzle orifice..... approximately 0.33mm (0.013 inch)
 - nozzle pressure 12 Mpa (1700 psi)
- **AIR SPRAY**
 - recommended thinner Industrial Enamel Thinner
 - volume of thinner up to 25%
 - nozzle orifice..... 1.5 - 1.8mm
 - nozzle pressure 0.3 - 0.4 MPa (50-60 psi)
- **CLEANING SOLVENT** Industrial Enamel Thinner

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

PACKAGING

4 litres, 20 litres

For the most up to date information contact Watty! Customer Service Hotline or visit the Watty! Website.

CUSTOMER SERVICE HOTLINE	Australia 132 101	New Zealand 0800 735 551
WEBSITE	http://www.watty.com.au	http://www.watty.co.nz

Watty! and Super Etch are registered trademarks of Watty! Australia Pty Ltd. ZINCALUME and COLORBOND are registered trademarks of Bluescope Steel Limited. Scotch-Brite is a registered trademark of the 3M Company

1. This information is provided with respect to the listed Watty! products. Watty! recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty!; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Watty! endeavours to update this information and maintain the accuracy and currency of its contents, Watty! cannot guarantee that the information provided is wholly comprehensive. 3. For all product and non-product related information, Watty! recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty! Office. 4. To the full extent permitted by law, Watty!'s liability for breach of a condition or warranty implied into the contract for sale between Watty! and you by law is limited at Watty!'s election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.
WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)