



**DESCRIPTION**

- an ultra premium, two-part recoatable isocyanate cured, acrylic polyurethane finish
- conforms to AS3750.6

**PRINCIPAL CHARACTERISTICS**

- excellent colour and gloss retention
- excellent resistance to exterior exposure
- superior colour reproducibility through intermix tinting system
- tough, flexible and abrasion resistant
- unlimited recoatability with suitable preparation
- high opacity white available for improved coverage
- range of hardeners and thinners available to provide flexibility in application
- resistant to splash of mineral and vegetable oils, white spirit, paraffins and aliphatic petroleum products
- resistant to splash of mild chemicals
- can be air dried or force dried up to 60°C on metal to improve throughput

Note: We advise that you test this product to determine if it is suitable for your particular use.

**COLOURS AND GLOSS**

- AS2700 colour card, high opacity white , jet black, coarse and fine metallic colours, full gloss

**BASIC DATA AT 25°C and 50% RELATIVE HUMIDITY**

- vehicle type ..... acrylic polyurethane
- mix ratio ..... 2A:1B by volume
- typical film thickness (per coat) ..... 25 microns (dry), 65 microns (wet)
- solids content ..... approx. 40% by volume
- theoretical spreading rate ..... 16 m<sup>2</sup>/L for 25 microns (dry)
- dust free ..... 30 minutes (standard hardener)  
15 minutes (fast hardener)
- touch dry after ..... 5 hours (standard hardener)  
3 hours (fast hardener)
- hard dry ..... 20 hours (standard hardener)  
10 hours (fast hardener)
- full cure after ..... 7 days
- recoat time ..... refer to instructions for use
- shelf life (cool, dry place) ..... at least 12 months in unopened container

**RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE**

- best coating performance will be obtained with the highest degree of surface preparation
- degrease thoroughly to remove all oil, grease and other surface contaminants
- mild steel; remove all rust and any loose material by wire brush or mechanical sander, prime with Colourthane Primer Filler
- non-ferrous metals, stainless steel, galvanised iron, ZINCALUME®, abrade using a Scotch-Brite® pad or wet and dry sandpaper. Do not use steel wool. Prime with WattyI Super Etch® Primer
- Colourthane can be applied to suitable existing finishes, provided they are degreased and sanded
- laminates (eg. Laminex®); mechanically sand with 320-400 grade abrasive
- substrate temperature should be at least 3°C above dew point
- relative humidity should not exceed 75% during application and before the dry to handle time

**INSTRUCTIONS FOR USE**

- mixing ratio by volume 2A:1B
- mix with Colourthane Standard or Fast Hardener
- induction time - none
- pot life at 25°C 4 hours (Standard Hardener), 2 hours (Fast Hardener) Do not use after this time even if the mix is still liquid
- stir the components and mixed product well using a mechanical mixer
- thin only with Colourthane Reducers (fast, standard, slow and extra slow)
- thinning recommendations are given as a guide and may vary depending upon substrate temperature and weather conditions
- for best results it is recommended to use slow reducer above 25°C and standard reducer below 20°C, blends of the two reducers can be used for intermediate temperatures
- the temperature of the mixed product must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in lower sag resistance and slower cure
- thinner should only be added after mixing the components
- freshly catalysed material should not be added to product that has been mixed for some time
- recoat times for wet on wet; allow for a flash-off time of 5 - 10 mins between coats, can be recoated within 8 hours without sanding. If recoating after 8 hours sand with P320 - P400 between coats. If higher gloss is required, a coat of Colourthane Clear may be applied as soon as the colour is dust free. If applied after the coating is hard dry, sand with P400 - P600 before clear coating
- for recommendations outside those contained in this data sheet, refer to Watty!

**APPLICATION**

- **AIRLESS SPRAY**
  - recommended thinner ..... Colourthane Reducer
  - volume of thinner ..... up to 5%
  - nozzle orifice ..... approximately 0.28mm (0.011 inch)
  - nozzle pressure ..... 15 MPa (2100 psi)
- **AIR SPRAY**
  - recommended thinner ..... Colourthane Reducer
  - volume of thinner ..... up to 10%
  - nozzle orifice ..... 1.2 - 1.5 mm
  - nozzle pressure ..... 350 - 450 kPa (50-60 psi)
- **CLEANING SOLVENT** ..... Colourthane Reducer

**SAFETY PRECAUTIONS**

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- contains 0.023% monomeric diisocyanate when mixed. Provide adequate ventilation during use. Breathing the vapour is dangerous. Avoid prolonged breathing of fumes. Where ventilation is poor or where applied by spray, use suitable respiratory equipment at all times
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

**ADDITIONAL DATA****Curing table - using Standard Hardener**

Substrate temperature	Dust free	Touch free	Dry to handle	Hard dry	Ready to sand
15°C	50 mins	8 hrs	16 hrs	24hrs	20 hrs
25°C	30 mins	5 hrs	12 hrs	20 hrs	16 hrs
60°C	5 mins	15 mins	40 mins	50 mins	45 mins

**Curing table - using Fast Hardener**

Substrate temperature	Dust free	Touch free	Dry to handle	Hard dry	Ready to sand
15°C	25 mins	5 hrs	8 hrs	16 hrs	12 hrs
25°C	15 mins	3 hrs	6 hrs	10 hrs	8 hrs
60°C	5 mins	10 mins	20 mins	25 mins	20 mins

- adequate ventilation must be continuously maintained during application and curing

**Pot life (at application viscosity)**

Paint temperature	Standard Hardener	Fast Hardener
15°C	6 hrs	3 hrs
25°C	4 hrs	2 hrs
35°C	2 hrs	1 hr

**PACKAGING**

Part A 1 litre, 4 litres, 20 litres

Part B 1 litre, 2 litres

For the most up to date information contact Watty Customer Service Hotline or visit the Watty Website.

CUSTOMER SERVICE HOTLINE  
WEBSITE

Australia  
132 101  
<http://www.watty.com.au>

New Zealand  
0800 735 551  
<http://www.watty.co.nz>

Watty, Colourthane and Super Etch are registered trademarks of Watty Australia Pty Ltd. Laminex is a registered trademark of The Laminex Group Pty. Ltd. Scotch-Brite is a registered trademark of the 3M Company. ZINCALUME is a registered trademark of Bluescope Steel Limited.

1. This information is provided with respect to the listed Watty products. Watty recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty cannot guarantee that the information provided is wholly comprehensive. 3. For all product and non-product related information, Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty Office. 4. To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.  
WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)