

# GranoSpray-On® Fine

Formerly GranoClassic

Page 1 of 2  
Resource Code 868201  
January 2011

## DESCRIPTION

- GranoSpray-On® Fine is a spray applied pigmented acrylic texture coating giving an elegant yet traditional stone-like finish.
- GranoSpray-On® Fine may be left matt or overcoated with GranoImpact® (G2.01) or GranoSkin® Membrane (5.02) for enhanced durability.

## PRINCIPAL CHARACTERISTICS

- Suitable for interior or exterior use.
- GranoSpray-On® Fine may be used to decorate, restore and protect commercial buildings, resorts, high-rise buildings, homes and offices.
- GranoSpray-On® Fine is an economical and long lasting means for creating lightweight stone-like finishes over most cementitious substrates.
- When spray applied, GranoSpray-On® Fine may be used to create carved stone-like effects for unusual shapes including simulated block outlines and mouldings.
- GranoSpray-On® Fine is water-based for applicator safety and ease of use.

## COLOURS AND GLOSS

- Off white. May be tinted as required. Refer to the Watty colour range including the authentic heritage range. May also be tinted to other competitor colour ranges through the Watty tinting system. It is recommended that, for exterior application, the light-fastness of the chosen colour be confirmed before ordering.
- Low sheen when overcoated by GranoImpact (G2.01), Satin when overcoated by GranoSkin Membrane (G2.14) or Matt when overcoated by GranoShield Matt (G2.27)

## BASIC DATA AT 25°C

- **Surface Dry** Four to six (4-6) hours
- **Topcoat** Twenty-four (24) hours
- **Fully Cured** Seven (7) days  
All figures are quoted at 25°C and 50% Relative Humidity. Drying will take longer at lower temperatures or higher relative humidity.
- **Density** 1.80 Kg/L
- **Consistency** Thick render like material
- **Texture** Weathered stone-like texture
- **Coverage per coat** 1.84 Kg/M<sup>2</sup>
- **Wet Film Thickness** 1020 microns (approx)
- **Dry Film Thickness** 670 microns (approx)
- **Moisture Control** Excellent, when topcoated, however the coating must not be subject to hydrostatic pressure.
- **Abrasion Resistance** Excellent
- **Thinning** Up to 10% water for spray application.
- **Early Fire Hazard (AS 1530.3)**

Ignitability	(0-20)	0
Spread of Flame	(0-20)	0
Heat Evolved	(0-10)	0
Smoke Developed	(0-10)	4
- **Clean-up** Thoroughly clean equipment with water.

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- GranoSpray-On® Fine may be applied to off-form concrete Class 2 (AS 1510) or equivalent, cement rendered fair-faced flush-jointed concrete block and brickwork (common, clay, concrete, Calsil®, and extruded), ExoTec®, CFC, and fibre cement sheeting, tilt-up and pre-cast concrete, Autoclaved Aerated Concrete (AAC).

### RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE - continued

- Make-good of substrate is necessary if substrate imperfections are to be eliminated. Please refer to separate Datasheets for GranoRender® (G1.10), GranoPatch® Smooth (G1.04), GranoPatch® Spackle (G1.05), or GranoReady Render® (G1.12).
- Surface Preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, application must be carried out according to Wattyl's recommendations.
- Ensure the surface is clean and dry. All substrates must be free of dirt, dust, grease, oil, mould release agents, bondbreakers and any other contaminants that may interfere with adhesion. Fresh cementitious substrates should be left for 14-28 days before coating. There must be less than 15% moisture content in the surface at the time of coating to ensure optimum coating performance.
- Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.
- Freshly applied material must be protected from frosts and rain for a minimum of forty eight (48) hours.
- Not suitable for walk on surfaces.
- For specific substrate preparation, see relevant specification sheets.

### INSTRUCTIONS FOR USE

- Stir contents thoroughly with a power stirrer before use.
- GranoSpray-On® Fine is applied by hopper gun. Spray one (1) dust coat and allow to dry for half an hour before applying the full wet coat. This is then left to dry for 24 hours prior to top coating.

#### HOPPER SPRAY GUN SETTINGS

Nozzle 4-6mm      Air Pressure 40-60 psi

- GranoSpray-On® Fine is overcoated with GranoImpact® (G2.01) or GranoSkin® Membrane (G2.14).

### SAFETY DATA

- **Caution**      Provide adequate ventilation during use.
- **Spills and Disposal**      Do not allow spilt material to enter drains or other watercourses. Absorb spills with sand or other inert material. Unwanted paint should be kept in a sealed container, such as an empty paint can, and disposed of via special waste collection services. Check with your local Council regarding the disposal of empty paint containers
- **M.S.D.S.**      A Material Safety Data Sheet (M.S.D.S.) is available on request.
- **First Aid**  
If swallowed **do not** induce vomiting. Give plenty of water to drink. Contact a doctor or the Poisons Information Centre. Phone 131126 (Australia).  
If in eyes, hold eyes open and flood with water for at least 15 minutes. Contact a doctor if any irritation occurs.  
If on skin remove contaminated clothing, wash skin thoroughly with soap and water or a proprietary skin cleanser. Do not use solvents.  
If affected by inhalation remove person to fresh air. If breathing difficulties persist or occur later, contact a doctor.

### ADDITIONAL DATA

- Available in 15 litre (27 Kg) containers.
- Containers must be secured and stored upright during transit.
- Containers must not be exposed to excessive heat or cold.
- Storage must be under cover, away from direct heat, freezing and moisture, in well-sealed containers.
- It is recommended that application be carried out by a skilled applicator, who is totally conversant with the GranoSite products and systems, to validate full material warranty conditions.
- For further information, contact the Wattyl Information Hotline. Phone 132101(Australia)

Calsil® is a registered trademark of Boral Resources (Vic) Pty Ltd  
ExoTec® is a registered trademark of James Hardie International Finance B.V.

1. This information is provided with respect to the listed GranoSite products. Wattyl recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
2. The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.
3. Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office.
4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.