

Granosite Texture Fine™

Page 1 of 2
Resource Code 861101
March 2008

DESCRIPTION

- Granosite Texture Fine™ is an acrylic, high performance coating applied by black texture roller or 18mm pile roller to achieve a medium or low profile texture.
- Granosite Texture Fine™ must be top coated with GranolImpact® (G2.01).

PRINCIPAL CHARACTERISTICS

- Suitable for interior or exterior use.
- Granosite Texture Fine™ systems have good adhesion to a wide variety of substrates.
- Granosite Texture Fine™ is well suited for high-traffic areas as it exhibits extremely good abrasion and impact resistance.
- Granosite Texture Fine™ is water-based for applicator safety and ease of use.

COLOURS AND GLOSS

- Bases may be tinted as required. Refer to the Watty colour range including the authentic heritage range. May also be tinted to other competitor colour ranges through the Watty tinting system.
- It is recommended that, for exterior application, the light-fastness of the chosen colour be confirmed before ordering.
- Matt, but requires topcoating with GranolImpact
- Low Sheen, when top coated with GranolImpact® (G2.01)

BASIC DATA AT 25°C

- **Surface Dry** Four (4) hours
 - **Topcoat** Twenty Four (24) hours
 - **Hard Dry** Seven (7) days
- All figures are quoted at 25°C and 50% Relative Humidity. Drying will take longer at lower temperatures or higher relative humidity.
- **Density** 1.7Kg/L
 - **Consistency** Thick, creamy paste.
 - **Texture** Medium or low profile texture
 - **Coverage per coat** 0.60 L/M²
 - **Wet Film Thickness** 600 microns (approx)
 - **Dry Film Thickness** 380 microns (approx)
 - **Moisture Control** Excellent, when topcoated, however the coating must not be subjected to hydrostatic pressure.
 - **Abrasion Resistance** Excellent
 - **Thinning** Not required
 - **Clean up** Thoroughly clean equipment with water.

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- Granosite Texture Fine™ may be applied to off-form concrete Class 2 (AS 1510) or equivalent, cement rendered fair-faced flush-jointed concrete block and brickwork (common, clay, concrete, Calsil®, and extruded), CFC, tilt-up and pre-cast concrete and paperfaced plasterboard. Make-good of substrate is necessary if substrate imperfections are to be eliminated. Please refer to separate Datasheets for GranoRender® (G1.10), GranoPatch® Smooth (G1.04), GranoPatch® Spackle (G1.05).
- Surface Preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, application must be carried out according to Watty's recommendations.
- Ensure the surface is clean and dry. All substrates must be free of dirt, dust, grease, oil, mould release agents, bondbreakers and any other contaminants that may interfere with adhesion. Fresh cementitious substrates should be left for 14-28 days before coating. There must be less than 15% moisture content in the surface at the time of coating to ensure optimum coating performance.

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE - continued

- Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.
- Freshly applied material must be protected from frosts and rain for a minimum of forty eight (48) hours.
- Not suitable for roofs, ponds etc or walk on surfaces.
- For specific substrate preparation, see relevant specification sheets.

INSTRUCTIONS FOR USE

- Stir contents thoroughly with a power stirrer before use.
- Granosite Texture Fine™ is applied in one (1) coat by medium black texture or 18mm pile roller to a correctly prepared and primed surface.
- Granosite Texture Fine™ must be over coated with GranolImpact (G2.01).
- Note: The texture achieved will vary depending on the supplier of the texture roller.

SAFETY DATA

- **Caution** Provide adequate ventilation during use.
- **Spills and Disposal** Do not allow spilt material to enter drains or other watercourses. Absorb spills with sand or other inert material. Unwanted paint should be kept in a sealed container, such as an empty paint can, and disposed of via special waste collection services. Check with your local Council regarding the disposal of empty paint containers
- **M.S.D.S.** A Material Safety Data Sheet (M.S.D.S.) is available on request.
- **First Aid**
If swallowed **do not** induce vomiting. Give plenty of water to drink. Contact a doctor or the Poisons Information Centre. Phone 131126 (Australia).
If in eyes, hold eyes open and flood with water for at least 15 minutes. Contact a doctor if any irritation occurs.
If on skin remove contaminated clothing, wash skin thoroughly with soap and water or a proprietary skin cleanser. Do not use solvents.
If affected by inhalation remove person to fresh air. If breathing difficulties persist or occur later, contact a doctor.

ADDITIONAL DATA

- Available in 15 litre containers.
- Containers must be secured and stored upright during transit.
- Containers must not be exposed to excessive heat or cold.
- Storage must be under cover, away from direct heat, freezing and moisture, in well-sealed containers.
- It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Granosite products and systems, to validate full material warranty conditions.
- For further information, contact the Watty! Information Hotline. Phone 132101(Australia).

Calsil® is a registered trademark of Boral Resources (Vic) Pty Ltd

1. This information is provided with respect to the listed Granosite products. Watty! recommends that:
(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty!; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
2. The information in this technical data sheet was prepared using information gathered during product development. While Watty! endeavours to update this information and maintain the accuracy and currency of its contents, Watty! cannot guarantee that the information provided is wholly comprehensive.
3. Watty! recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty! Office.
4. To the full extent permitted by law, Watty!'s liability for breach of a condition or warranty implied into the contract for sale between Watty! and you by law is limited at Watty!'s election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.