



**DESCRIPTION**

- an economical, single-pack, anticorrosive zinc phosphate primer for steel

**PRINCIPAL CHARACTERISTICS**

- a primer offering good performance when used alone or under interior and exterior grade high gloss enamels
- easily applied using either conventional or airless spray
- a protective coating for structural steelwork, machinery, cranes etc
- can be left untopcoated for a serviceable finish, or may be overcoated with a WattyI industrial enamels

Note: We advise that you test this product to determine if it is suitable for your particular use.

**COLOUR AND GLOSS**

- red, grey, satin

**BASIC DATA AT 25°C and 50% RELATIVE HUMIDITY**

- vehicle type ..... modified polymer
- typical film thickness (per coat) ..... 25 microns (dry), 75 microns (wet)
- solids content ..... approx. 35% by volume
- theoretical spreading rate ..... 14m<sup>2</sup>/L for 25 microns (dry)
- touch dry..... 1-2 hours
- dry to handle ..... 4-8 hours
- hard dry ..... 24 hours
- re-coat time ..... minimum 16 hours
- shelf life (cool, dry place) ..... at least 12 months in unopened container

Note: Due to the nature of the manufacturing process some variation in colour and drying characteristics may be experienced between batches

**RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE**

- best coating performance will be obtained with the highest degree of surface preparation
- degrease thoroughly to remove all oil, grease and other surface contaminants
- mild steel; remove all rust and any loose material by wire brush or mechanical sander
- suitable previous coat; mechanically sand with P220-240 grit sandpaper
- substrate temperature shall be at least 3°C above dew point
- relative humidity should not exceed 85%

**INSTRUCTIONS FOR USE**

- stir thoroughly with a flat-bladed or mechanical stirrer before, and during use
- paint temperature must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in low sag resistance and slower cure
- overcoat with WattyI Agricultural, Structural or All Purpose Enamel
- adequate ventilation must be continuously maintained during application and curing
- for recommendations outside those contained in this data sheet, refer to WattyI



**APPLICATION**

- **AIRLESS SPRAY**
  - recommended thinner .... Industrial Enamel Thinner
  - volume of thinner ..... up to 5%
  - nozzle orifice..... approx 0.46 mm (0.018 inch)
  - nozzle pressure ..... 15 MPa (2100 psi)
  
- **AIR SPRAY**
  - recommended thinner .... Industrial Enamel Thinner
  - volume of thinner ..... up to 15%
  - nozzle orifice..... 1.5 - 2 mm
  - nozzle pressure ..... 350 - 450 kPa (50-60 psi)
  
- **CLEANING SOLVENT** ..... Industrial Enamel Thinner

**SAFETY PRECAUTIONS**

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

**PACKAGING**

20 litres

For the most up to date information contact Watty Customer Service Hotline or visit the Watty Website.

	<b>Australia</b>	<b>New Zealand</b>
<b>CUSTOMER SERVICE HOTLINE</b>	<b>132 101</b>	<b>0800 735 551</b>
<b>WEBSITE</b>	<a href="http://www.wattyl.com.au">http://www.wattyl.com.au</a>	<a href="http://www.wattyl.co.nz">http://www.wattyl.co.nz</a>

Watty is a registered trademark of Watty Australia Pty Ltd.

1. This information is provided with respect to the listed Watty products. Watty recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty cannot guarantee that the information provided is wholly comprehensive. 3. For all product and non-product related information, Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty Office. 4. To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.  
WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)