



DESCRIPTION

- a quick drying durable solvent borne road marking paint

PRINCIPAL CHARACTERISTICS

- suitable for line marking use on highways, city and suburban streets, intersections, parking lots, factory floors etc.
- excellent durability
- formulated to give high wear resistance
- high speed line application using airless application with glass bead deposition - speed 20-30 km/hour
- stencil application at intersections
- suitable for use on all types of road surfaces both bituminous and concrete
- suitable for use with or without glass beads

Note: We advise that you test this product to determine if it is suitable for your particular use.

COLOURS AND GLOSS

- white, yellow, flat

BASIC DATA AT 25°C and 50% RELATIVE HUMIDITY

- vehicle type alkyd
- typical film thickness (per coat) 150 microns (dry), 375 microns (wet)
- solids content approx. 40% by volume
- theoretical spreading rate 2.7 m²/L for 150 microns (dry)
- touch dry after 3 minutes
- no pick up time 10 minutes
- recoat time minimum 10 minutes
- shelf life (cool, dry place) at least 12 months in unopened container

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- bituminous and concrete road surfaces; substrate must be dry and free from dirt, grease, oil etc, sweep clean of excess dirt and dust prior to painting
- do not paint over soft bitumen or new concrete (allow 28 days cure)
- substrate temperature should be at least 3°C above dew point
- relative humidity should not exceed 85%
- do not apply at air temperatures below 10°C

INSTRUCTIONS FOR USE

- stir thoroughly with a flat-bladed or mechanical stirrer before, and during use
- paint temperature must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in low sag resistance and slower cure
- adequate ventilation must be continuously maintained during application and curing
- suitable for use with coated or uncoated glass beads (0.3 - 0.5mm). Beads may be added by pre-mixing or by a drop on process during paint application. Deposition rate 275-325g/m² (730-860g/litre)
- for recommendations outside those contained in this data sheet, refer to Watty!



APPLICATION

- **AIRLESS SPRAY**
 - recommended thinner not required - product is ready for use
 - volume of thinner n/a
 - nozzle orifice..... approximately 0.47- 0.53mm (0.019-0.021 inch)
 - nozzle pressure up to 17-21 MPa (2600-3000 psi)

- **AIR SPRAY**
 - recommended thinner Thinner T2
 - volume of thinner up to 30%
 - nozzle orifice..... 1.8 - 2.0mm
 - nozzle pressure 350 - 450 kPa (50-60 psi)

- **CLEANING SOLVENT** Thinner T2

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

PACKAGING

20 litres, 200 litres (white only)

For the most up to date information contact Wattyl Customer Service Hotline or visit the Wattyl Website.

	Australia	New Zealand
CUSTOMER SERVICE HOTLINE	132 101	0800 735 551
WEBSITE	http://www.wattyl.com.au	http://www.wattyl.co.nz

Wattyl® is a registered trademark of Wattyl Australia Pty Ltd.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive. 3. For all product and non-product related information, Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office. 4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.

WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)